



Technical parameter	Standard	Unit	Result
DESCRIPTION			
Construction			heterogeneous
Total thickness	EN 428	mm	2,5
Wear layer thickness	EN 429	mm	0,7
Width of roll	EN 426	m	2 , 4
Length of roll	EN 426	lm	20
Total weight	EN 430	kg/m2	2,4
CLASSIFICATION			
Product specification	EN 651		✓
European classification	EN 685	class	34/42
Residual indentation	EN 433	max. mm	0,1
Dimensional stability	EN 434	max.%	0,2
Light fastness	EN 20105 B02	grade	6
PERFORMANCE			
Abrasion group	MSZ EN 660-1	class	T
Fire resistance	EN 13501-1	class	Cfl-s1
Impact sound reduction	EN ISO 140-8	DL _w (dB)	14
Slip resistance	DIN 51130		R9
Electrical resistance	EN 1815	kV	< 2
	EN 1081	Ω	≤ 10 ¹⁰
Chemical resistance	EN 423		✓
Bacterial resistance	EN ISO846:1999		✓
Castor chair resistance	EN 425		✓
Anti-bacterial and fungicid treatment			graboSAN
Enviromental attributes			Solvent and heavy metal free product
Seaming method			heat or cold weld
Warranty		year	7
CE MARKING	EN 14041		✓